



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME: YELLOW 10830

CAS NO.:5567-15-7

C.I NO.: PY83

Molecular Formula: C<sub>36</sub>H<sub>32</sub>CL<sub>4</sub>N<sub>6</sub>O<sub>8</sub>

QUANTITY : STANDARD

Molecular Weight:818.49

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.50
Water Soluble Matter %	≤1.00
Oil Absorption ml/100g	35-45
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	200'c
Light resistance	6
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	