



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: RED 3003

CAS NO.: 2425-85-6

C.I NO.: PR.3

Molecular Formula: C₁₇H₁₃N₃O₃

QUANTITY : STANDARD

Molecular Weight: 307.30

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.00
Water Soluble Matter %	≤1.00
Oil Absorption ml/100g	30-40
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	140'c
Light fastness	5
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	