



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME:RED 3146R

CAS NO.:5280 -68-2

C.I NO.:PR.146

Molecular Formula: C<sub>33</sub>H<sub>27</sub>ClN<sub>4</sub>O<sub>6</sub>

QUANTITY : STANDARD

Molecular Weight:611.04

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.50
Water Soluble Matter %	≤1.5
Oil Absorption ml/100g	40-50
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	180'c
Light fastness	5
Acid resistance	4
Alkali resistance	4
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	