



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: YELLOW 10013

CAS NO.:2512-29-01

C.I NO.: PY1

Molecular Formula: C₁₇H₁₆N₄O₄

QUANTITY : STANDARD

Molecular Weight:340.33

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.00
Water Soluble Matter %	≤1.50
Oil Absorption ml/100g	25-35
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.0-7.0
Heat resistance	140'c
Light resistance	6
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	