



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME:RED 3112

CAS NO.:6535-46-2

C.I NO.:PR.112

Molecular Formula: C<sub>24</sub>H<sub>16</sub>Cl<sub>3</sub>N<sub>3</sub>O<sub>2</sub>

QUANTITY : STANDARD

Molecular Weight:485.76

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.00
Water Soluble Matter %	≤1.5
Oil Absorption ml/100g	30-40
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	4.5-5.5
Heat resistance	140°c
Light fastness	6
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	3
THIS PIGMENT CONTAINS NO ANILINE	