



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME: RED 3482P

CAS NO.:7023-61-2

C.I NO.:PR.48:2

Molecular Formula: C<sub>18</sub>H<sub>11</sub>ClN<sub>2</sub>O<sub>6</sub>SCa

QUANTITY : STANDARD

Molecular Weight:458.90

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤3.00
Water Soluble Matter %	≤2.50
Oil Absorption ml/100g	45-55
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	7.5-8.5
Heat resistance	180'c
Light fastness	6
Acid resistance	3
Alkali resistance	3
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	