



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME:RED 31702

CAS NO.:2786-76 -7

C.I NO.:PR.170

Molecular Formula: C₂₆H₂₂N₄O₄

QUANTITY : STANDARD

Molecular Weight:454.48

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.00
Water Soluble Matter %	≤1.00
Oil Absorption ml/100g	35-45
Electric Conductivity us.cm	≤500
Fineness 120mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	180'c
Light fastness	5
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	4
THIS PIGMENT CONTAINS NO ANILINE	