



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: RED 3002

CAS NO.:6041-94-7

C.I NO.:PR.2

Molecular Formula: C₂₃H₁₅Cl₂N₃O₂

QUANTITY : STANDARD

Molecular Weight:436.29

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.00
Water Soluble Matter %	≤1.50
Oil Absorption ml/100g	45-55
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	150'c
Light fastness	6
Weather fastness	5
Acid resistance	4
Alkali resistance	5
Water base resistance	5
Oil resistance	3
THIS PIGMENT CONTAINS NO ANILINE	