



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME: YELLOW 10033

CAS NO.:6486-23-3

C.I NO: PY3

Molecular Formula: C<sub>16</sub>H<sub>12</sub>Cl<sub>2</sub>N<sub>4</sub>O<sub>4</sub>

QUANTITY: STANDARD

Molecular Weight:395.20

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.00
Water Matter % Soluble	≤1.50
Oil Absorption ml/100g	25-35
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	6.5-7.5
Heat resistance	160'c
Light fastness	6
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	4
THIS PIGMENT CONTAINS NO ANILINE	