



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: Yellow 1074G

CAS NO.:6358-31-2

C.I NO.: PY74

Molecular Formula: C₁₈H₁₈N₄O₆

QUANTITY : STANDARD

Molecular Weight:386.36

| ITEMS OF SPECIFICATION | STANDARD |
|----------------------------------|-----------|
| Shade (Against Standard) | |
| Tint % | 100±5 |
| Moisture % | ≤2.0 |
| Water Matter % Soluble | ≤1.5 |
| Oil Absorption ml/100g | 35-45 |
| Electric Conductivity us.cm | ≤500 |
| Fineness (80mesh) % | ≥95% pass |
| PH Value | 6.0-7.0 |
| Heat resistance | 140'c |
| Light resistance | 6 |
| Acid resistance | 5 |
| Alkali resistance | 5 |
| Water base resistance | 5 |
| Oil resistance | 5 |
| THIS PIGMENT CONTAINS NO ANILINE | |