



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME:RED 35318

CAS NO.:5160-02-01

C.I NO.:PR.53:1

Molecular Formula: $C_{34}H_{24}Cl_2N_4O_8S_2Ba$

QUANTITY : STANDARD

Molecular Weight:888.98

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.50
Water Soluble Matter %	≤2.00
Oil Absorption ml/100g	40-50
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	7.0-8.0
Heat resistance	220'c
Light fastness	5
Acid resistance	3
Alkali resistance	3
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	