



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: RED 3571D

CAS NO.:5281-04-9

C.I NO.:PR.57:1

Molecular Formula: $C_{18}H_{12}N_2O_6SCa$

QUANTITY : STANDARD

Molecular Weight:424.46

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤2.00
Water Soluble Matter %	≤2.50
Oil Absorption ml/100g	45-55
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	7.0-8.0
Heat resistance	200'c
Light fastness	5
Acid resistance	3
Alkali resistance	3
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	