



## ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

### TECHNICAL DATA SHEET

PRODUCT NAME: VIOLET 60195

CAS NO.:1047-16-1

C.I NO.:PV.19

Molecular Formula:  $C_{20}H_{12}N_2O_2$

QUANTITY : STANDARD

Molecular Weight:312.32

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.50
Water Soluble Matter %	≤1.50
Oil Absorption ml/100g	45-55
Electric Conductivity us.cm	≤500
Fineness (120mesh) %	≥95% pass
PH Value	7.0-8.0
Heat resistance	300'c
Light fastness	8
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	