



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME: ORANGE 2034P

CAS NO.:15793-72-4

C.I NO.: PO34

Molecular Formula: C₃₄H₂₈CL₂N₈O₂

QUANTITY : STANDARD

Molecular Weight:651.60

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	
Tint %	100±5
Moisture %	≤1.50
Water Soluble Matter %	≤1.50
Oil Absorption ml/100g	40-50
Electric Conductivity us.cm	≤500
Fineness (60mesh) %	≥95% pass
PH Value	6.0-7.0
Heat resistance	180°C
Light fastness	6
Acid resistance	5
Alkali resistance	5
Water base resistance	5
Oil resistance	5
THIS PIGMENT CONTAINS NO ANILINE	