



ZHEJIANG AURIC TECHNOLOGY CO., LTD

Tel : 86-571-83822028

Fax: 86-571-83822028

mail: sales@auric-tech.com

Web: www.auric-tech.com

Zuoyou Business Center, Ningwei street, Xiaoshan district, Hangzhou city, Zhejiang province, China

TECHNICAL DATA SHEET

PRODUCT NAME:RED 34918

CAS NO.:1103 -38-4

C.I NO.: PR.49:1

Molecular Formula: C₄₀H₂₆N₄O₈S₂^{1/2}Ba

QUANTITY : STANDARD

Molecular Weight:822.16

ITEMS OF SPECIFICATION	STANDARD
Shade (Against Standard)	similar
Tint %	100±5
Moisture %	≤4.50
Water Soluble Matter %	≤2.50
Oil Absorption ml/100g	45-55
Electric Conductivity us.cm	≤500
Fineness (80mesh) %	≥95% pass
PH Value	7.0-8.0
Heat resistance	160'c
Light fastness	3
Acid resistance	3
Alkali resistance	3
Water base resistance	5
Oil resistance	3-4